

Title	Reactivity of syringyl quinone methide intermediates in dehydrogenative polymerization I: high-yield production of synthetic lignins (DHPs) in horseradish peroxidase-catalyzed polymerization of sinapyl alcohol in the presence of nucleophilic reagents
Author(s)	Tobimatsu, Yuki; Takano, Toshiyuki; Kamitakahara, Hiroshi; Nakatsubo, Fumiaki
Citation	Journal of Wood Science (2010), 56(3): 233-241
Issue Date	2010-06
URL	http://hdl.handle.net/2433/128637
Right	The original publication is available at www.springerlink.com
Type	Journal Article
Textversion	author

Reactivity of syringyl quinone methide intermediates in dehydrogenative polymerization. Part
1. High yield production of synthetic lignins (DHPs) in horseradish peroxidase-catalyzed
polymerization of sinapyl alcohol in the presence of nucleophilic reagents.

Yuki Tobimatsu, Toshiyuki Takano*, Hiroshi Kamitakahara, Fumiaki Nakatsubo

Division of Forest & Biomaterials Science, Graduate School of Agriculture, Kyoto University,
Sakyo-ku, Kyoto, 606-8502, Japan

*Corresponding author: Mailing Address: Division of Forest & Biomaterials Science, Graduate
School of Agriculture, Kyoto University, Kitashirakawa-oiwakecho, Sakyo-ku, Kyoto, 606-8502,
Japan; Tel: +81-75-753-6254; Fax: +81-75-753-6300; E-mail: takatmys@kais.kyoto-u.ac.jp

Key words: Dehydrogenation polymer (DHP); Horseradish peroxidase (HRP); nucleophilic
addition; Quinone methide; Syringyl lignin

Note: This report follows the previous rapid communication “Azide ion as a quinone methide
scavenger in the horseradish peroxidase-catalyzed polymerization of sinapyl alcohol”, J Wood Sci
(2008) 54:87-89

1 **Abstract**

2 It is known that the conventional dehydrogenative polymerization of sinapyl alcohol
3 (S-alc) gave syringyl synthetic lignins (S-DHPs), but in extremely low yields. In this article, to
4 examine the contribution of syringyl quinone methide intermediates (S-QM) on S-DHP production,
5 horseradish peroxidase (HRP)-catalyzed dehydrogenative polymerization of S-alc was carried out in
6 the presence of nucleophilic reagents that promote the rearomatization of S-QM. First, the
7 HRP-catalyzed polymerization of sinapyl alcohol γ -O- β -D-glucopyranoside (isosyringin, iso-S),
8 which allows us to monitor the polymerization process in a homogeneous aqueous phase, was
9 utilized for screening of a nucleophile used as an S-QM scavenger. Monitoring of the iso-S
10 polymerization in the presence of various nucleophilic reagents by UV spectroscopy and gel
11 permeation chromatography with photodiode array detection (GPC-PDA) revealed a high ability of
12 azide ion to convert oligomeric S-QM efficiently to S-DHP. Accordingly, azide ion was utilized as
13 an S-QM scavenger in HRP-catalyzed polymerization of S-alc, which resulted in high yield
14 production of S-DHPs (~83%), as expected. The ^1H -, ^{13}C - and 2D-HSQC NMR investigations on
15 the resulting S-DHPs clearly demonstrated that azide ion efficiently performed nucleophilic
16 additions to the C- α of S-QM during the polymerization. These results provide experimental proof
17 that the low reactivity of S-QM with nucleophiles (such as water, phenolic and aliphatic hydroxyl
18 groups) in the conventional polymerization system critically impedes the production of S-DHPs
19 from S-alc.

20

1 **Introduction**

2 The last stage of lignin formation in plant cell wall can be mimicked *in vitro* by the
3 enzymatic dehydrogenative polymerization of monolignols [*p*-coumaryl alcohol (H-alc); coniferyl
4 alcohol (G-alc); sinapyl alcohol (S-alc)], leading to the lignin polymer models (dehydrogenation
5 polymers, DHPs).¹⁻³ As reviewed by several authors,⁴⁻⁸ much of what is now known about the lignin
6 polymerizations is based on the studies of this system. However, a satisfactory synthesis of DHPs
7 structurally resembling native lignins has not been achieved yet, implying that the polymerization
8 process is not fully understood. One of the open questions with this regard is the peculiar
9 polymerization behavior of S-alc, being completely different from those of H-alc and G-alc. Many
10 researchers have reported that enzymatic dehydrogenative polymerization of S-alc afforded syringyl
11 (S)-DHPs, but with low molecular masses in low yields, while H-alc and G-alc readily gave
12 *p*-hydroxyphenyl (H)- and guaiacyl (G)-DHPs, respectively, with high molecular masses in high
13 yields.⁹⁻¹⁵

14 As well established, the dehydrogenative polymerization of S-alc basically consisting of
15 three reaction steps as depicted in Fig. 1: step 1: enzymatic radical formations; step 2: radical
16 couplings; step 3: rearomatization of syringyl quinone methide intermediates (S-QM) by
17 nucleophilic additions of nucleophiles in the polymerization system. Several problems in each
18 reaction step have been discussed in connection with the low polymerizability of S-alc: the low
19 reactivity of common oxidants such as horseradish peroxidase (HRP) / hydrogen peroxide to S-type
20 phenolic compounds for step 1¹⁶⁻²⁰ and preferential β - β coupling reactions to β -O-4 for step 2.²⁰⁻²²
21 So far, little attention has been paid to step 3 in connection with the low polymerizability of S-alc *in*
22 *vitro*.

1 Recently, we have investigated on the HRP-catalyzed polymerization of sinapyl alcohol
2 γ -O- β -D-glucopyranoside [isosyringin (iso-S), Fig. 2] as a model reaction system to study the
3 polymerization behavior of S-alc.^{15,23-27} Owing to the presence of a highly hydrophilic sugar unit
4 attached to S-alc, the polymerization of iso-S gives water-soluble products in a homogeneous
5 aqueous phase, whereas the conventional polymerization of S-alc gives water-insoluble products in
6 a heterogeneous way. It was also confirmed that the reactivity and polymerization behavior of iso-S
7 in the dehydrogenative polymerization are well reflected by those of S-alc. This unique
8 polymerization system based on iso-S enabled us to follow the time-course of S-DHP formation in a
9 homogeneous aqueous media by such as UV spectroscopy²⁶ and gel permeation chromatography
10 with photodiode array detection (GPC-PDA).²⁷ Importantly, our approach has revealed that
11 oligomeric S-QM accumulates stably during the HRP-catalyzed polymerization of iso-S. The low
12 reactivity of S-QM can be explained by the presence of two electron-donating methoxyl groups,
13 which reduce the positive charge density at the α -positions. It is reported that the analogous quinone
14 methide, 2,6-di-*tert*-butyl-4-methylene-2,5-cyclohexadienone also reacts very slowly in aqueous
15 media. Bolton et al. pointed out that this low reactivity is due to the lack of hydrogen bonding
16 between the shielded oxo group and water molecules, suppressing charge separation of the quinone
17 methide.^{28,29} The same explanation can be applied for the low reactivity of S-QM.

18 The data in our previous studies strongly suggest that the low reactivity of S-QM with
19 nucleophiles in the conventional polymerization system (at step 3 in Fig. 1) may retard the
20 subsequent polymerization for S-DHP formation from S-alc. Based on this concept, if suitable
21 nucleophiles with high nucleophilicity towards S-QM are added to the conventional polymerization
22 system, they can perform nucleophilic additions to promote the rearomatization of S-QM and the

subsequent polymerization steps in Fig. 1 would repeatedly proceed to yield S-DHPs efficiently. In the preliminary study, we showed that the HRP-catalyzed polymerization of S-alc in the presence of nucleophilic azide ion gave S-DHPs in significantly high yield.³⁰ In this article, further data on S-DHP formations in the presence of nucleophilic reagents are presented.

Experimental

Materials

Iso-S,²³ S-alc,³¹ and syringylglycerol- β -syringyl ether [1-(4-hydroxy-3,5-dimethoxyphenyl)-2-(2,6-dimethoxyphenoxy)-propane-1,3-diol (**1**)]^{32,33} were synthesized according to the method described in literature. HRP (100 U mg⁻¹) was purchased from Wako Pure Chemicals (Kyoto, Japan) and used without further purification. Wakogel C-200 (Wako Pure Chemicals) was used in silica gel column chromatography. Other chemicals were purchased from Nacalai Tesque Inc. (Kyoto, Japan) or Wako Pure Chemicals and used as received.

Screening of nucleophile for HRP-catalyzed polymerization of S-alc by monitoring iso-S polymerization in the presence of nucleophilic reagents

UV spectroscopic monitoring of HRP-catalyzed polymerization of iso-S in the presence of nucleophiles was carried out as follows.²⁶ The solution (3 ml) consisting of 100 μ M iso-S, 1500 μ g l⁻¹ HRP and 100-1000 μ M nucleophilic reagents (D-glucuronic acid, ethyl amine, sodium sulfite,

1 potassium iodide, cysteine and sodium azide) in 50 mM sodium phosphate buffer (pH6.5) and the
2 same solution without monomer were placed in a sample cell and a reference cell, respectively. The
3 cells were set in a JASCO V-560 spectrophotometer and kept at 25°C under stirring. The
4 polymerization was initiated by adding 25 µl 0.024% hydrogen peroxide aqueous solution (final
5 concentration: 60 µM) to the sample cell, and UV spectra were recorded at a regular time interval
6 (scan rate, 2000 nm min⁻¹; scan region, 250-400 nm; data interval, 1 nm; response mode, quick).

7 GPC-PDA monitoring of the HRP-catalyzed polymerization of iso-S in the presence of
8 azide ion was done as follows.²⁷ Three solutions were prepared for the polymerization of iso-S:
9 solution A, 2.0 mg of HRP in 500 µl of 0.05 M phosphate buffer (pH 6.5); solution B, 20 µmol of
10 the glycosides in 2500 µl of the buffer; solution C, 2500 µl aqueous solution containing sodium
11 azide (20 µmol) and hydrogen peroxide (24 µmol). Polymerization was initiated by adding
12 solutions B and C simultaneously to solution A at a constant rate (2.5 ml h⁻¹; monomer addition
13 time, 60 min). After initiating the polymerization, reaction mixtures (100 µl) were periodically
14 sampled and mixed with 900 µl of 0.1M LiCl in dimethylformamide (DMF) to terminate the
15 reaction, immediately cooled at 0°C, and subjected to the GPC-PDA analyses within 15 min after
16 withdrawing from the reaction mixture. The GPC-PDA analyses were performed on a Shimadzu
17 LC-20A LC system (Shimadzu, Japan) equipped with a SPD-M20A photodiode array detector.
18 Elution conditions were as follows: column, TSK gel α-M (Tosoh, Japan); eluent, 0.1 M LiCl in
19 DMF; flow rate, 0.5 ml min⁻¹; column oven temperature, 40°C; injection volume, 20 µl. Conditions
20 for PDA detection were as follows: scan region: 260-400 nm; band width, 4 nm; response, 1280 ms.
21 Molecular weight calibration was made using polystyrene standards (Shodex, Japan). Data
22 acquisition and computation utilized LCsolution version 1.22 SP1 software (Shimadzu, Japan).

HRP-catalyzed polymerization of S-alc in the presence of azide ion

Two solutions were prepared for polymerization of S-alc: solution A, 120 ml of distilled water containing 0.5 mmol S-alc and 3-12 mg of HRP; solution B, 120 ml of 0.019% hydrogen peroxide (0.6 mmol) aqueous solution containing 0.5 mmol sodium azide. Solutions A and B were added drop-wise to 30 ml of 0.1 M phosphate buffer over a period of 0.5-48 h. The precipitate of the resulting polymer was collected by centrifugation (12000 rpm, 10 min), washed twice with distilled water and lyophilized to obtain S-DHP.

S-DHPs were acetylated with standard protocols¹⁵ and subjected to GPC and nuclear magnetic resonance (NMR) analyses. GPC was performed with a Shimadzu LC-10 system equipped with a UV-Vis detector (SPD-10Avp, monitoring at 280 nm) under the following conditions: columns, K-802, K-802.5 and K-805 (Shodex, Japan); eluent, CHCl₃; flow rate, 1.0 ml min⁻¹; column temperature, 40 °C. The system was calibrated with polystyrene standards (Shodex). ¹H-, ¹³C-, and two-dimensional (2D)-heteronuclear single quantum coherence (HSQC) NMR spectra were collected with a Varian INOVA300 FT-NMR spectrometer (300 and 75.5 MHz for ¹H and ¹³C nuclei, respectively) in chloroform-*d* with tetramethylsilane as the internal standard (0.0 ppm). Chemical shifts (δ) and coupling constants (*J*) were given in δ -values (ppm) and hertz (Hz), respectively.

3-azido-3-(4-hydroxy-3,5-dimethoxyphenyl)-2-(2,6-dimethoxyphenoxy)-1-propanol (**3**)

1 The quinone methide **2** was prepared from syringylglycerol- β -syringyl ether (**1**) by the
2 method in literature.^{34,35} Briefly, compound **1** (380 mg, 1.0 mmol) was dissolved in 10 ml of
3 dichloromethane and to this solution 260 μ l of trimethylsilyl bromide (2.0 mmol) was added with
4 stirring under nitrogen at room temperature. After 1 min, the solution was poured into a separation
5 funnel and extracted twice with 30 ml saturated sodium bicarbonate aqueous solution. The organic
6 layer was dried over sodium sulfate and evaporated to dryness. Obtained raddish colored solid of
7 compound **2** was dissolved in 5 ml of anhydrous dioxane and added dropwise into 4 ml of
8 dioxane/water solution (1:1, v/v) containing sodium azide (650 mg, 10 mmol) at 0 °C under
9 nitrogen. After 1 h, the reaction mixture was extracted with ethyl acetate and washed twice with
10 saturated sodium chloride aqueous solution, and dried over sodium sulfate. Evaporation in vacuo
11 produced an orange oil, which was purified by a silica gel column chromatography [eluent, ethyl
12 acetate/n-hexane (3:2, v/v)] to give compound **3** as white solid (192.7 mg, 48% yield, *erythro*/*threo*
13 = ~1.0). Stereochemical assignments were made from ¹H-NMR signals of propyl side-chain protons
14 in analogy with the data of β -O-4 lignin model compounds in literature.^{36,37}

15 Acetate of compound **3**; ¹H-NMR (in CDCl₃): δ 1.96 (3H, s, C _{γ} -OCOCH₃, *erythro* isomer),
16 1.98 (3H, s, C _{γ} -OCOCH₃, *threo* isomer), 2.33 (3H, s, C₄-OCOCH₃), 3.77-3.82 (3.77, 3.80, 3.81,
17 3.82) (12H, s, Ar-OMe), 3.84-3.93 (1H, m, H _{γ 1}), 4.25-4.33 (1H, m, H _{γ 2}), 4.39-4.53 (1H, m, H _{β}),
18 4.91 (0.5H, d, J = 6.6 H _{α} , *erythro* isomer), 5.01 (1H, d, J = 4.8 H _{α} , *threo* isomer), 6.55 (2H, d, J =
19 3.0, H_{2'} and H_{6'}, *threo* isomer), 6.58 (2H, d, J = 3.0, H_{2'} and H_{6'}, *erythro* isomer), 6.65 (2H, s, H₂
20 and H₆, *threo* isomer), 6.71 (2H, s, H₂ and H₆, *erythro* isomer), 7.00 (1H, t, J = 8.7, H_{1'}, *erythro*
21 isomer), 7.01 (1H, t, J = 8.7, H_{1'}, *threo* isomer). ¹³C-NMR: δ 20.3, 20.6 (COCH₃), 55.8, 56.0, 56.1
22 (Ar-OMe), 62.7 (C _{γ} , *erythro* isomer), 63.1 (C _{γ} , *threo* isomer), 66.2 (C _{α} , *erythro* isomer), 66.7 (C _{α} ,

threo isomer), 81.2 (C_β, *erythro* isomer), 81.9 (C_β, *threo* isomer), 103.8 (C₂ and C₆, *threo* isomer), 104.2 (C₂ and C₆, *erythro* isomer), 104.6 (C_{2'} and C_{6'}, *erythro* isomer), 104.9 (C_{2'} and C_{6'}, *threo* isomer), 124.1 (C_{1'}), 128.1 (C₄, *erythro* isomer), 128.5 (C₄, *threo* isomer), 134.7 (C₁), 135.1 (C_{4'}, *erythro* isomer), 135.2 (C_{4'}, *threo* isomer), 151.9 (C₃ and C₅, *erythro* isomer), 152.0 (C₃ and C₅, *threo* isomer), 153.2 (C_{3'} and C_{5'}), 168.5 (Ar-OCOCH₃), 170.3, 170.7 (C_γ-OCOCH₃)

Results and Discussions

Screening of nucleophile for HRP-catalyzed polymerization of S-alc

In previous studies, we successfully detected and characterized S-QM formed in the HRP-catalyzed polymerization of iso-S using UV spectroscopic²⁶ and GPC-PDA²⁷ measurements. In the present study, these techniques were applied for screening of nucleophile used as an S-QM scavenger in the polymerization of S-alc.

UV spectroscopic monitoring of HRP-catalyzed polymerization of iso-S in the presence of nucleophilic reagents

Figure 3A shows the time-depended changes in UV spectra during the HRP-catalyzed polymerization of iso-S without nucleophiles. As the reaction time increased, the absorbance peak at 274 nm decreased, indicating that iso-S was oxidized by HRP. Formation and accumulation of stable S-QM were clearly indicated by the appearance of the absorption peak at 325 nm, as evidenced in our previous study.²⁶ A suitable nucleophile should not retard the HRP-catalyzed

1 oxidation of iso-S, which can be evaluated by the decrease of the absorption at 274 nm (A_{274}), and
2 the one should suppress the accumulation of S-QM, which can be evaluated by the increase of
3 absorptions at 325 nm (A_{325}). Representative nucleophilic reagents investigated here are carboxyl
4 acid (D-glucronic acid), amine (ethyl amine), sulfite ion (sodium sulfite), iodide ion (pottasium
5 iodide), thiol (cysteine) and azide ion (sodium azide). Figure 4 displays plots of A_{274} and A_{325} during
6 iso-S polymerizations in the presence of the nucleophilic reagents. In polymerization with
7 carboxylic acid, amine, sulfite ion and iodide ion, A_{274} decreased smoothly, but A_{325} increased
8 significantly, indicating high levels of S-QM accumulation (Fig. 4B-E). These results indicate that
9 the nucleophilicity of these compounds toward S-QM is not sufficient under the present conditions.
10 In several reports, highly nucleophilic thiol compounds³⁸⁻⁴⁰ and azide ion⁴¹⁻⁴³ were used to trap QM
11 species formed as reactive intermediates in various chemical reactions. On the other hands, both
12 these are well-known peroxidase inhibitors.⁴⁴ When iso-S polymerization was conducted in the
13 presence of cysteine (Fig. 4F), the decreasing of A_{274} was much slower at the initial stage of
14 polymerization (~30min), while the increase in A_{325} was suppressed in this period. After a period of
15 reaction time, A_{274} suddenly dropped and then A_{325} started increasing. Thiol compounds are reported
16 to be substrates for HRP.^{45,46} The result obtained here can be explained by that HRP-catalyzed
17 oxidation of cysteine took place in advance of the oxidation of iso-S. Thus, thiol compounds seem
18 to be unsuitable as a S-QM scavenger used in HRP-catalyzed polymerization. On the other hand,
19 A_{274} decreased smoothly in the presence of sodium azide, whereas the increasing in A_{325} was hardly
20 observed (Figs. 3B and 4G). The results indicated that azide ion efficiently scavenges S-QM
21 without significant inhibition to the catalytic ability of HRP. Therefore, azide ion was concluded to

be the most suitable nucleophile as a S-QM scavenger used in HRP-catalyzed polymerization of S-alc.

GPC-PDA monitoring of HRP-catalyzed polymerization of S-alc in the presence of azide ion

The HRP-catalyzed polymerization of iso-S in the presence of azide ion was monitored by GPC-PDA to obtain further confirmation of the ability of azide ion to trap S-QM. This method permits to follow the changes of the molecular weights of S-DHP intermediates as well as the formation of oligomeric S-QM during the course of the iso-S polymerization.²⁷ Figure 5 shows the GPC-PDA profiles of the iso-S polymerization in the absence and presence of azide ion. In the absence of azide ion, the presence of oligomeric S-QM was clearly indicated by the intense peak detected at 344 nm at 19.2 min of elution time (peak top MW = 1700) (Fig. 5A). As Fig. 5C shows, in the absence of azide ion, the peak area detected at 344 nm rose significantly just after initiating the polymerization and then decreased very slowly as reaction time progressed, indicating the transient but stable presence of oligomeric S-QM. In contrast, during the polymerization in the presence of azide ion, the peak area from S-QM remained constantly low, indicating that accumulations of the oligomeric S-QM were effectively suppressed (Fig. 5B,C). This finding agrees well with the results in UV spectroscopic monitoring of the polymerization described above. Formation of polyphenolic S-DHP could be followed by the absorption at 274 nm. The product molecular weights calculated based on PDA detection at 274 nm are plotted against reaction time in Fig. 5D. Clearly, the addition of azide ion to the polymerization system resulted in efficient formation of polyphenolic S-DHP, as the product molecular mass increased faster in polymerization with azide ion than without azide ion. These results are readily rationalized if the oligomeric S-QM

are rapidly converted to the corresponding phenolics by azide addition and the resulting phenolics react further to produce S-DHP.

HRP-catalyzed polymerization of S-alc in the presence of azide ion

HRP-catalyzed polymerization of S-alc in the presence of azide ion, which serves as a S-QM scavenger, was carried out under various polymerization conditions. Figure 6 shows the effect of azide ion on the yield of isolated S-DHPs. The yield of S-DHPs prepared according to the so-called bulk polymerization method,² in which the monomer is added to the polymerization system drop-wise but rapidly in 0.5 h, was much affected by the amount of sodium azide added to the polymerization system (Fig. 6A). As expected from earlier studies,⁹⁻¹⁵ in the absence of azide ion, the yield of S-DHP was quite low (~5%). As amount of sodium azide was upped to 1 eq. for S-alc, the yield of S-DHP greatly increased to 54 %. When excess amount of sodium azide for S-alc was applied, however, the yield of S-DHP dropped again probably due to inactivation of HRP induced by azide ion. Then, the so-called end-wise polymerization method,² in which the monomer is added to the polymerization system slowly for 24-48 h, was employed with 1eq. of sodium azide for S-alc. Figure 6B shows the effect of monomer addition time on the yield of S-DHP. The yield of S-DHP with azide ion further increased to 83% as the monomer addition time increased to 48 h, while the yield of S-DHP without azide ion also increased but to no more than 12%. Table 1 lists the average molecular weights (M_n and M_w) and their distributions (M_w/M_n) of S-DHPs. The M_n values of the acetylated samples of S-DHPs prepared with azide ion were 1300-1800 (degree of polymerization, $DP = 4-6$), which are in the same range as those reported for the conventional

DHPs.^{47,48} The end-wise polymerization method contributed to an increase in the molecular mass of S-DHP. It was observed that M_n and M_w/M_n values of the isolated S-DHPs prepared with azide ion were slightly lower than those for S-DHPs prepared without azide ion. This may be explained by structural differences between them, as discussed in the next section. Nevertheless, it is obvious that appropriate amount of azide ion (1 eq. for S-alc) significantly promotes the production of S-DHP, indicating that the low reactivity of S-QM with nucleophiles is critically responsible for the low yield of S-DHP in the conventional polymerization system.

Structural characterization of S-DHPs

The ^1H -, ^{13}C -, and 2D-HSQC NMR spectra of acetylated S-DHPs prepared in the absence and presence of azide ion (prepared based on Table 1 entry 3) are shown in Fig. 7. Nucleophilic attacks of azide ion to S-QM during the polymerization are clearly demonstrated by the appearance of the signals from β -O-4/ α -N₃ structure (**I**), which are identical to the data for α -azide model compound **3** synthesized according to Fig. 8. All the spectra indicate that the contributions from β -O-4/ α -OH (**II**) and β -O-4/ α -ether substructures (**III**) are negligibly small for S-DHP obtained with azide ion, whereas the both structures are abundant for the conventional S-DHP prepared without azide ion. This result suggests that during the polymerization of S-alc with nucleophilic azide ion, the β -O-4 S-QM are exclusively quenched by azide ion but not by water, phenolic or aliphatic hydroxyl groups. A series of peaks from β - β resinol structure (**IV**) is also observed in the spectra of S-DHP obtained with azide ion, indicating that β - β S-QM are rapidly trapped by intramolecular γ -hydroxyl groups even in the presence of azide ion. Our preliminary data of Fourier

transform-infrared (FT-IR) and matrix-assisted laser desorption ionization time-of-flight mass spectrometry (MALDI-TOF MS analyses of S-DHPs also support this result.³⁰ As expected from these data, S-DHP prepared in the presence of azide ion is a simply linear polymer made up mainly of structure **I** and **IV**. As already mentioned, the S-DHPs prepared with azide ion tend to have slightly lower molecular masses and narrower molecular mass distributions than those of conventional S-DHPs (see Table 1). This difference might be explained by the lack of the structure **III** in the S-DHPs prepared with azide ion, as the branching structure **III** is formed by nucleophilic attacks of oligomeric phenolics onto β -O-4 S-QM.

Conclusion

To examine the contribution of reactivity of S-QM on S-DHP production from S-alc, HRP-catalyzed dehydrogenative polymerization in the presence of nucleophilic reagents was investigated. The HRP-catalyzed polymerization of iso-S, which permits to monitor the formation of S-QM in a homogeneous aqueous phase, was successfully utilized for screening of nucleophile used as a S-QM scavenger in the polymerization of S-alc. UV spectroscopic monitoring of iso-S polymerization in the presence of various nucleophiles revealed the high ability of azide ion to trap S-QM without significant inhibition to HRP activity. GPC-PDA monitoring of the polymerization of iso-S also demonstrated that the oligomeric S-QM efficiently converted to S-DHP in the presence of azide ion. Accordingly, azide ion was applied as a S-QM scavenger in HRP-catalyzed polymerization of S-alc, resulting in production of S-DHPs in remarkably high yields. Although azide ion dramatically promotes the production of S-DHP, the molecular masses of the isolated

S-DHPs was not improved so much, which is partly explained by the lack of branching α -O-4 structures (**III**) in the S-DHPs prepared with azide ion. NMR analyses on S-DHPs clearly demonstrated that azide ion efficiently performed nucleophilic additions to the C- α of the S-QM during the polymerization. It was demonstrated that, in the HRP-catalyzed polymerization of S-alc in the presence of strongly nucleophilic azide ion, S-QM are readily rearomatized by azide addition. Then, subsequent polymerization steps, initiated by the oxidation of the re-generated phenolic hydroxyl groups, can proceed repeatedly to yield S-DHPs efficiently. Consequently, these data provide experimental proof that the low reactivity of S-QM with nucleophiles in the conventional polymerization system is a crucial cause of the low efficiency in the dehydrogenative polymerization of S-alc *in vitro*. Because there seems to be no evidence that any particular nucleophilic reagents operate in lignin formations *in vivo*, subsequent studies should focus on the reactions of S-QM under various polymerization conditions without the use of strongly nucleophilic reagents. Such studies are expected to provide new clues for understanding the factors controlling lignin polymerization in the plant cell.

Acknowledgements

This research was supported by a Grant-in-Aid for Young Scientists (#20-2841) from the Japan Society for the Promotion of Science (JSPS).

1 **References**

- 2 1. Freudenberg K (1965) Lignin. Its constitution and formation from *p*-hydroxycinnamyl
3 alcohols. *Sci* 148:595-600
- 4 2. Sarkanen KV (1971) Precursors and their polymerization. In: Sarkanen KV, Ludwig CH (eds)
5 Lignins—occurrence, formation, structure and reactions. Wiley, New York, pp 95-163
- 6 3. Higuchi T (1990) Lignin biochemistry: Biosynthesis and biodegradation. *Wood Sci Technol*
7 24:23-63
- 8 4. Boerjan W, Ralph J, Baucher M (2003) Lignin biosynthesis. *Annu Rev Plant Biol* 54:519-546
- 9 5. Ralph J, Lundquist K, Brunow G, Lu F, Kim H, Schatz PF, Marita JM, Hatfield RD, Ralph
10 SA, Christensen JH, Boerjan W (2004) Lignins: Natural polymers from oxidative coupling of
11 4-hydroxyphenylpropanoids. *Phytochem Rev* 3:29-60
- 12 6. Monties B (2005) Biological variability of lignins. *Cellul Chem Technol* 39:341-367
- 13 7. Grabber JH (2005) How do lignin composition, structure, and cross-linking affect
14 degradability? A review of cell wall model studies. *Crop Sci* 45:820-831
- 15 8. Ralph J, Brunow G, Harris PJ, Dixon RA, Schatz PF, Boerjan W (2008) Lignification: are
16 lignins biosynthesized via simple combinatorial chemistry or via proteinaceous control and
17 template replication? *Recent Adv Polyphenol Res* 1:36-66
- 18 9. Freudenberg K, Hübner HH (1952) Hydroxycinnamyl alcohols and their dehydrogenation
19 polymers. *Chem Ber* 85:1181-1191
- 20 10. Yamasaki T, Hata K, Higuchi T (1976) Dehydrogenation polymer of sinapyl alcohol by
21 peroxidase and hydrogen peroxide. *Mokuzai Gakkaishi* 22:582-588
- 22 11. Faix O, Besold G (1978) Preparation and characterization of dehydrogenation polymers of

p-hydroxycinnamic alcohols (DHP's) particularly made from pure 4-hydroxyphenyl-(H-), guaiacyl-(G-) and syringyl-(S-) propane polymers. I. Elemental analysis and determination of functional groups. *Holzforschung* 32:1-7

12. Weymouth N, Dean J FD, Eriksson KEL, Morrison WH III, Himmelsbach DS, Hartley RD (1993) Synthesis and spectroscopic characterization of *p*-hydroxyphenyl, guaiacyl and syringyl lignin polymer models (DHPs). *Nord Pulp Pap Res J* 8:344-349

13. Sterjiades R, Dean JFD, Gamble G, Himmelsbach DS, Eriksson KEL (1993) Extracellular laccases and peroxidases from sycamore maple (*Acer pseudoplatanus*) cell-suspension cultures. Reactions with monolignols and lignin model compounds. *Planta* 190:75-87

14. Yoshida S, Chatani A, Tanahashi M, Honda Y, Watanabe T, Kuwahara M (1998) Preparation of synthetic lignin by manganese peroxidase of *Bjerkandera adusta* in organic solvents. *Holzforschung* 52:282-286

15. Tobimatsu Y, Takano T, Kamitakahara H, Nakatsubo F (2008) Studies on the Dehydrogenative Polymerizations of Monolignol β -glycosides. Part 3: Horseradish peroxidase-catalyzed polymerizations of triandrin and isosyringin. *J Wood Chem Technol* 28:69-83

16. Ostergaard L, Teilum K, Mirza O, Mattsson O, Petersen M, Welinder KG, Mundy J, Gajhede M, Henriksen A (2000) Arabidopsis ATP A2 peroxidase. Expression and high-resolution structure of a plant peroxidase with implications for lignification. *Plant Mol Biol* 44:231-243

17. Nielsen KL, Indiani C, Henriksen A, Feis A, Becucci M, Gajhede M, Smulevich G, Welinder KG (2001) Differential activity and structure of highly similar peroxidases. Spectroscopic, crystallographic, and enzymatic analyses of lignifying *Arabidopsis thaliana* peroxidase A2

and horseradish peroxidase A2 Biochem 40:11013-11021

18. Aoyama W, Sasaki S, Matsumura S, Mitsunaga T, Hirai H, Tsutsumi Y, Nishida T (2002)

Sinapyl alcohol-specific peroxidase isoenzyme catalyzes the formation of the dehydrogenative polymer from sinapyl alcohol. J Wood Sci 48:497-504

19. Sasaki S, Nishida T, Tsutsumi Y, Kondo R (2004) Lignin dehydrogenative polymerization mechanism: a poplar cell wall peroxidase directly oxidizes polymer lignin and produces in vitro dehydrogenative polymer rich in β -O-4 linkage. FEBS Letters 562:197-201

20. Kobayashi T, Taguchi H, Shigematsu M, Tanahashi M (2005) Substituent effects of 3,5-disubstituted *p*-coumaryl alcohols on their oxidation using horseradish peroxidase-H₂O₂ as the oxidant. J Wood Sci 51:607-614

21. Tanahashi M, Takeuchi H, Higuchi T (1976) Dehydrogenative polymerization of 3,5-substituted *p*-coumaryl alcohols. Wood Res 61:44-53

22. Tanahashi M, Higuchi T (1990) Effect of the hydrophobic regions of hemicelluloses on dehydrogenative polymerization of sinapyl alcohol. Mokuzai Gakkaishi 36:424-428

23. Takano T, Tobimatsu Y, Hosoya T, Hattori T, Ohnishi J, Takano M, Kamitakahara H, Nakatsubo F (2006) Studies on the dehydrogenative polymerizations of monolignol β -glycosides. Part 1. Syntheses of monolignol β -glycosides, (*E*)-isoconiferin, (*E*)-isosyringin, and (*E*)-triandrin. J Wood Chem Technol 26:215-229

24. Tobimatsu Y, Takano T, Kamitakahara H, Nakatsubo F (2006) Studies on the dehydrogenative polymerizations of monolignol β -glycosides. Part 2: horseradish peroxidase-catalyzed dehydrogenative polymerization of isoconiferin. Holzforschung 60:513-518

- 1 25. Tobimatsu Y, Takano T, Kamitakahara H, Nakatsubo F (2008) Studies on the
2 dehydrogenative polymerizations (DHPs) of monolignol β -glycosides: part 4. Horseradish
3 peroxidase-catalyzed copolymerization of isoconiferin and isosyringin. *Holzforschung*
4 62:495-500
- 5 26. Tobimatsu Y, Takano T, Kamitakahara H, Nakatsubo F (2008) Studies on the
6 dehydrogenative polymerization of monolignol β -glycosides: part 5. UV spectroscopic
7 monitoring of horseradish peroxidase-catalyzed polymerization of monolignol glycosides.
8 *Holzforschung* 62:501-507
- 9 27. Tobimatsu Y, Takano T, Kamitakahara H, Nakatsubo F Studies on the dehydrogenative
10 polymerizations of monolignol β -glycosides. Part 6. Monitoring of horseradish
11 peroxidase-catalyzed polymerization of monolignol glycosides by GPC-PDA. *Holzforschung*
12 (in press)
- 13 28. Bolton JL, Sevestre H, Ibe BO, Thompson JA (1990) Formation and reactivity of alternative
14 quinone methides from butylated hydroxytoluene: possible explanation for species-specific
15 pneumotoxicity. *Chem Res Toxicol* 3:65-70
- 16 29. Bolton J L, Valerio LGJ, Thompson JA (1992) The enzymic formation and chemical
17 reactivity of quinone methides correlate with alkylphenol-induced toxicity in rat hepatocytes.
18 *Chem Res Toxicol* 5:816-822
- 19 30. Tobimatsu Y, Takano T, Kamitakahara H, Nakatsubo F (2008) Azide ion as a quinone
20 methide scavenger in the horseradish peroxidase-catalyzed polymerization of sinapyl alcohol.
21 *J Wood Sci* 54:87-89
- 22 31. Quideau S, Ralph J (1992) Facile large-scale synthesis of coniferyl, sinapyl, and p-coumaryl

1 alcohol. J Agric Food Chem 40:1108-1110

2 32. Nakatsubo F, Sato K, Higuchi T (1975) Synthesis of guaiacylglycerol- β -guaiacyl ether.
3 Holzforschung 29:165-168

4 33. Sipilä J, Syrjanen K (1995) Synthesis and ^{13}C NMR spectroscopic characterization of six
5 dimeric arylglycerol- β -aryl ether model compounds representative of syringyl and
6 *p*-hydroxyphenyl structures in lignins. On the aldol reaction in β -ether preparation.
7 Holzforschung 49:325-331

8 34. Ralph J, Young RA (1983) Stereochemical aspects of addition reactions involving lignin
9 model quinone methides. J Wood Chem Technol 3:161-181

10 35. Brunow G, Sipilä J, Makela T (1989) On the mechanism of formation of noncyclic benzyl
11 ethers during lignin biosynthesis. Part 1. The reactivity of β -O-4-quinone methides with
12 phenols and alcohols. Holzforschung 43:55-9

13 36. Hauteville M, Lundquist K, VonUnge S (1986) NMR studies of lignins. 7. Proton NMR
14 spectroscopic investigation of the distribution of *erythro* and *threo* forms of β -O-4 structures
15 in lignins. Acta Chem Scand B, B40:31-35

16 37. Toikka M, Sipilä J, Teleman A, Brunow G (1998) Lignin-carbohydrate model compounds.
17 Formation of lignin-methyl arabinoside and lignin-methyl galactoside benzyl ethers via
18 quinone methide intermediates. J Chem Soc Perkin Trans, 1:3813-3818

19 38. Ramakrishnan K, Fisher J (1983) Nucleophilic trapping of 7,11-dideoxyanthracyclinone
20 quinone methides. J Am Chem Soc 105:7187-7188

21 39. Fisher J, Abdella B R, McLane K E (1985) Anthracycline antibiotic reduction by spinach
22 ferredoxin-NADP⁺ reductase and ferredoxin. Biochem 24:3562-3571

- 1 40. Awad HM, Boersma M G, Vervoort J, Rietjens I M C M (2000) Peroxidase-catalyzed
2 formation of quercetin quinone methide-glutathione adducts. Arch Biochem Biophys
3 378:224-233
- 4 41. Al Kazwini AT, O'Neill P, Cundall RB, Adams GE, Junino A, Maignan J (1992) Direct
5 observation of the reaction of the quinonemethide from 5,6-dihydroxyindole with the
6 nucleophilic azide ion. Tetrahedron Lett 33:3045-3048
- 7 42. Novak M, Kayser KJ, Brooks ME (1998) Azide and solvent trapping of electrophilic
8 intermediates generated during the hydrolysis of *N*-(sulfonatoxy)-*N*-acetyl-4-aminostilbene.
9 J Org Chem 63:5489-5496
- 10 43. Richard JP, Toteva MM, Crugeiras J (2000) Structure-reactivity relationships and intrinsic
11 reaction barriers for nucleophile additions to a quinone methide: A strongly
12 resonance-stabilized carbocation. J Am Chem Soc 122:1664-1674
- 13 44. Veitch N C (2004) Horseradish peroxidase: a modern view of a classic enzyme. Phytochem
14 65:249-259
- 15 45. DeRycker J, Halliwell B (1978) Oxidation of thiol compounds by catalase and peroxidase in
16 the presence of manganese (II) and phenols. Biochem Soc Trans 6:1343-1345
- 17 46. Burner U, Obinger C (1997) Transient-state and steady-state kinetics of the oxidation of
18 aliphatic and aromatic thiols by horseradish peroxidase. FEBS Lett. 411:269-274
- 19 47. Faix O, Lange W, Besold G (1981) Molecular weight determinations of DHP'S from mixtures
20 of precursors by steric exclusion chromatography (HPLC). Holzforschung 35:137-40
- 21 48. Cathala B, Saake B, Faix O, Monties B (1998) Evaluation of the reproducibility of the
22 synthesis of dehydrogenation polymer models of lignin. Polym Degrad Stab 59:65-69

1 **Figure and scheme legends**

2

3 **Figure 1** The dehydrogenative polymerization of sinapyl alcohol (S-alc) via β -O-4
4 couplings.

5

6 **Figure 2** Chemical structures of sinapyl alcohol (S-alc) and isosyringin (iso-S) (sinapyl
7 alcohol γ -O- β -D-glucopyranoside).

8

9 **Figure 3** UV spectra of the polymerization mixtures during the HRP-catalyzed
10 polymerizations of isosyringin (iso-S). **A** In the absence of nucleophiles. Reaction
11 time: 0, 2, 6, 10, 16, 20 and 30 min. **B** In the presence of azide ion (1eq. for iso-S).
12 Reaction time: 0, 2, 6, 10, 16, 10, 20 and 30 min.

13

14

15 **Figure 4** Changes of the absorbance at 274 nm (A_{274} , ○) and at 344 nm (A_{325} , ●) during the
16 HRP-catalyzed polymerizations of iso-S (100 μ M) in the presence of various
17 nucleophilic reagents: A: none (control); B: D-Glucronic acid (1000 μ M); C:
18 Ethyl amine (1000 μ M); D: Sodium sulfite (500 μ M); E: Pottasium iodide (1000
19 μ M); F: Cysteine (100 μ M); G: Sodium azide (NaN_3 , 100 μ M).

20

21 **Figure 5** GPC-PDA monitoring of the HRP-catalyzed polymerization of iso-S. **A**
22 Three-dimensional (3D) PDA plots in polymerization without nuceophilic regents.

B 3D PDA plots in polymerization with azide ion (1eq. for iso-S). **C** Plots of peak area detected at 344 nm over reaction time. **D** Plots of number and weight average molecular weights (M_n and M_w) calculated based on PDA detection at 274 nm over reaction time.


Figure 6 Yields of syringyl dehydrogenation polymers (S-DHPs) in the HRP-catalyzed polymerization of S-alc in the presence of azide ion. **A** Effect of the amount of sodium azide (HRP = 6 mg for 1 mmol S-alc; monomer addition time = 0.5 h). **B** Effect of the monomer addition time (HRP = 24 mg for 1 mmol S-alc; sodium azide = 1 eq. for S-alc).

Figure 7 Nuclear magnetic resonance (NMR) characterizations of acetylated S-DHPs from S-alc synthesized in the presence of azide ion. **A** ^1H -NMR spectra. **B** ^{13}C -NMR spectra. **C** 2D-heteronuclear single quantum coherence (HSQC) spectra.

Figure 8 Synthetic scheme for model compound **3**. TMS, trimethylsilyl

1 (Figure 1)

2




3

4

5

1 (Figure 2)

2



3 Sinapyl alcohol (**S-alc**)

Isosyringin (**iso-S**)


4

5

6

1 (Figure 3)

2



3

4

5

2




4

5

1 (Figure 5)

2



3



4

5

6

1 (Figure 6)

2




3

4


5

1 (Figure 7)


(A) $^1\text{H-NMR}$



(B) $^{13}\text{C-NMR}$




(C) HSQC



1 (Figure 8)

2



3

4

1 (Table 1)

2

Table 1 HRP-catalyzed polymerizations of sinapyl alcohol (S-alc) in the presence and the absence of sodium azide

Entry	HRP ^a (mg)	Monomer addition time (h)	Without N ₃ ⁻				With N ₃ ⁻ (1eq. for S-alc)			
			Yield (%)	<i>M_n</i> ^b × 10 ⁻³	<i>M_w</i> / <i>M_n</i> ^b	<i>DP_n</i> ^c	Yield (%)	<i>M_n</i> ^b × 10 ⁻³	<i>M_w</i> / <i>M_n</i> ^b	<i>DP_n</i> ^c
1	6	0.5	4.8	1.4	2.5	4.8	54.2	1.3	1.3	4.4
2	24	0.5	7.0	1.8	2.1	6.1	68.3	1.4	1.3	4.8
3	24	24	10.8	2.1	1.9	7.1	76.0	1.6	1.2	5.4
4	24	48	11.5	2.1	2.0	7.1	82.5	1.8	1.2	6.1

^a per 1 mmol of S-alc

^b determined by GPC after acetylation

^c calculated based on the molecular weight of sinapyl alcohol diacetate

3

4

5